

OVERVIEW

Terraroc MC is a high performance shrinkage compensated micro-concrete for partial or total replacement of deteriorated concrete. Because of its excellent fluidity it is suitable for congested areas where steel reinforcements make access difficult.

PROPERTIES

Terraroc MC is a pre-mixed blend of special cements, precisely graded aggregate, plasticizers and shrinkage compensating additives with the following properties.

- Ready to use
- Shrinkage compensated
- Factory controlled mix design
- Low water demand ensures durability and high ultimate strength
- Self compacting formulation
- High bond strength

AREAS OF USE

Terraroc MC is designed for use as part of the Terraco concrete repair system as a partial or total replacement of deteriorated concrete, in thickness in excess of 40mm. It is used to repair columns, beams, parapets and other concrete elements.

PREPARATION OF SURFACE

Do not apply at temperatures below 5°C. Remove all defective concrete back to the reinforcements, treat reinforcements with Epiprime ZR (see separate data sheet). Avoid feather edging. Place form-work to effect repair and treat with suitable mould release agent. The substrate should be saturated with water several hours before Terraroc MC is poured. Ensure all excess water is removed before pouring.

MIXING

Ensure that the mixing water is constant for each bag of compound (3.2ltr water/25kg Terraroc MC). A mechanical mixer is necessary to ensure consistency of the final mix. Add the powder to the water and mix continuously for 3 to 5 minutes.

PLACEMENT / CURING

Terraroc MC should be placed within 30 minutes of mixing. Avoid cold joints by pouring each repair in a single operation. Form-work can be removed when strength has reached approx. 10N/mm² and curing should be carried out according to normal concrete practice.

Clean tools and equipment with water after use.

HEALTH & SAFETY

Avoid prolonged contact with eyes and skin. For detailed information refer to relevant material safety data sheet.

PACKAGING & STORAGE

Terraroc MC is packed in 25kg valve craft bags.

Terraroc MC should be stored in a clean dry area protected from direct sunlight and extreme heat and cold. The pallets can be stacked two high provided care is taken. Opened sacks should be used first. Unopened sacks can be stored for 6 months. Use oldest material first.

TERRACO offers a comprehensive range of products and services for most concrete and finishing needs. Please contact the TERRACO Technical Service Department or your local TERRACO agent for further information, samples, demonstrations and instructor services. The information given in this leaflet is based upon laboratory research, as well as extensive field work and application. All products are sold subject to standard conditions of sale which are available on request. This information is based on TERRACO's present state of knowledge and is intended to provide general information on TERRACO's products and their methods of use. The prospective user is recommended to determine the suitability of TERRACO's suggestions and products before adopting them on a commercial scale.

TECHNICAL DATA

Product	High performance micro-concrete.
Binder	Hydraulic
Colours	Grey
Compressive Strength	45 n/mm ² (7 days), 60 N/mm ² (28 days).
Set Time	5 hours (initial), 8 hours (final).
Wet Density	2250 kg/m ³
Water Demand	13% (3.2 ltr water/25kg bag).
Application Thickness	>40mm.
Yield	25kg of powder + 3.2ltr of water gives 12.5ltr of mix.
Packaging	25kg valve craft bags.
Storage	6 months in original unopened container.

For technical enquiries please contact your nearest Terraco representative:

RUSSIA:

OOO Terraco Sweden Ltd, Russia
Tel: +7 095 101 2237
Fax: +7 095 927 3881
E-mail: terraco@online.ru
Web: www.terraco.ru

OOO Terraco Vostok Ltd

Tel: +7 (0)4212 431 933
Fax: +7 (0)4212 431 977
E-mail: terracoVostok@terraco.khn.ru

CHINA:

Terraco Architectural Coatings China Co., Ltd.
Tel: +86 (0)20 8758 2600,
Fax: +86 (0)20 8526 8056
E-mail: sales@terraco.com.cn
Web: www.terraco.com.cn

Terraco Chemical (Shanghai) Co., Ltd.

Tel: +86 (0)21 6210 2048
Fax: +86 (0)21 6252 0547
Email: sales@terraco.com.cn

JORDAN:

Jordan Swedish Polymers Industrial Corp.
Tel: +962 (0)6 552 7140, 553 0229, 551 4037
Fax: +962 (0)6 553 6560
E-mail: terraco@nol.com.jo
Web: www.terraco.jo

EGYPT:

Terraco Egypt Chemical Industries S.A.E.
Tel: +20 (0)2 8340 004, 832 3584
Fax: +20 (0)2 8340 004, 832 3584
E-mail: terraco@terraco.com.eg

UAE:

Terraco UAE Ltd
Tel: +971 (0)6 543 3565
Fax: +971 (0)6 543 3558
E-mail: terraco@emirates.net.ae

TURKEY:

Terraco Yapi Malzemeleri Sanayi Ve Ticaret AS
Tel: +90 (0)222 236 0423
Fax: +90 (0)222 236 0425
E-mail: terraco@terraco.com.tr
Web: www.terraco.com.tr

THAILAND:

Terraco Industry (Thailand) Limited
Tel: +66 (0)2 948 5558
Fax: +66 (0)2 948 5540
E-mail: terraco@terraco.co.th

VIETNAM:

Terraco Vietnam Co., Ltd
Tel: +84 (0)650 820100
Fax: +84 (0)650 820101
E-mail: terraco_vietnam@hcm.vnn.vn

SOUTH KOREA:

Terraco Korea Co., Ltd
Tel: +82 (0)43 645 8814
Fax: +82 (0)43 643 9429
E-Mail: terraco@terraco.co.kr
Web: www.terraco.co.kr

IRELAND:

Terraco Technical Centre, Ireland
Tel: +353 (0) 404 66555
Fax: +353 (0) 404 66654
E-mail: terraco@eircom.net
Web: www.terraco.com